


TEST REPORT

NO: 20241118006

Description: Electro Galvanized Wire Rope		Construction	6*7+FC
Size	3 MM	Lay Type	Right
Length	100 M	Tensile Strength	1570N/MM2
Actual Measured Breaking Strength of Rope		475 KG	
Working Load of Rope		95 KG	
<div>NOTE: 1. Any quality problem, please indicate this Certificate No..</div> <div>2. During the storage and transportation, please don't approach the acid, alkali and other harmful material.</div> <div>3. In the process of using, the user should often inspect the rope whether there is the damage.</div> <div>4. The rope inspection period should not exceed one year.</div> <div>If the storage time has exceeded one year, the user must inspect the rope again before the using.</div> <div></div>			

Inspector: MRS. HUANG

