

KARTA TECHNICZNA / TECHNICAL DATASHEET 140715

2,5 /3 EST

- 100% FLAX YARN DRY-SPUN FLAX ROVING
 100% HEMP YARN WET-SPUN FLAX LOW TWIST YARN
 BLEND: FLAX / PA6
 FLAX / PES

| PARAMETER | Nm real | Force avg [N] | CV force [%] | Elongation avg [%] | RKM min | RKM 3 points min | RKM max | RKM avg |
|-----------|-------------|---------------|--------------|--------------------|--------------|------------------|--------------|--------------|
| X | 0,83 | 201,62 | 12,23 | 3,72 | 12,31 | 12,73 | 22,02 | 17,09 |
| SD | - | 22,25 | 1,57 | 0,09 | 0,74 | 1,01 | 0,18 | 1,89 |
| CV | - | 11,03 | 12,84 | 2,47 | 5,97 | 7,95 | 0,83 | 11,05 |
| min | 0,83 | 185,89 | 11,12 | 3,65 | 11,79 | 12,01 | 21,89 | 15,75 |
| max | 0,8 | 217,35 | 13,34 | 3,78 | 12,83 | 13,44 | 22,15 | 18,42 |