

KARTA TECHNICZNA / TECHNICAL DATASHEET 140610

9,5/4 LEMLYS

- ☒ 100% FLAX YARN ☒ DRY-SPUN ☐ FLAX ROVING
☐ 100% HEMP YARN ☐ WET-SPUN ☐ FLAX LOW TWIST YARN
☐ BLEND: ☐ FLAX / PA6
 ☐ FLAX / PES

PARAMETER	Nm real	Force avg [N]	CV force [%]	Elongation avg [%]	RKM min	RKM 3 points min	RKM max	RKM avg
X	2,37	99,82	12,13	2,81	16,92	17,85	30,95	24,13
SD	0,00	6,55	1,37	0,77	2,07	1,86	2,11	1,58
CV	0,17	6,56	11,26	27,49	12,22	10,43	6,81	6,56
min	2,37	88,96	10,77	1,69	14,18	15,30	28,07	21,51
max	2,4	105,96	14,11	4,11	19,01	19,78	34,23	25,62